



STONETECH® BulletProof® Sealer

STONETECH® BulletProof® Sealer is an advanced sealer, designed to provide maximum protection on natural stone against the toughest oil and water-based stains.

**Globally Proven
Construction Solutions**



FEATURES/BENEFITS

- Maximum protection against most stains
- Advanced penetrating microbond protection
- Preserves natural look of stone
- Water-based formula
- Interior and exterior

PACKAGING

- 473 ml, 12 units per Case
- 946 ml, 6 units per Case
- 3.8 L, 4 units per Case
- 18.9 L, 1 units per Case
- 208 L, 1 unit per Case (lead time required)

USES (EXTERNAL)

- Countertops
- Splashbacks
- Floors
- Walls

RECOMMENDED SURFACES

Natural stone and Masonry Surfaces such as:

- Honed or Textured Marble
- Textured or Veined Granite
- Limestone
- Bluestone
- Travertine
- Sandstone
- Flagstone
- Quartzite
- Saltillo Tile

Best suited for the most porous stone surfaces

MANUFACTURER

LATICRETE Australia Pty Ltd
29 Telford Street
Virginia, QLD 4014 Australia

Telephone: 07 3865 1599
Toll Free: 1800 331 012
Fax: 07 3865 2250
Internet: www.laticrete.com.au

Approximate Coverage

Depending on stone type, texture and porosity; the site conditions at the time of installation; and the method of installation, the following rates of coverage will vary.

- Up to 10 m²/473 mL, for a single coat application
- Up to 22 m²/946 mL, for a single coat application
- Up to 84 m²/3.8 L, for a single coat application
- Up to 418 m²/18.9 L, for a single coat application
- Up to 4,599 m²/208L, for a single coat application

Expected Wear

- Up to 5 years on interior surfaces
- Up to 3 years on exterior surfaces

For best results, reapply annually.

VOC Content

<400 g/L (excluding water) for EPA Purposes

<10 g/L (including water) for LEED and Greenstar purposes (Low Solids Coating)

Storage and Handling Instructions

Avoid prolonged exposure to vapours. Use in a well-ventilated area. Do not ingest. Avoid contact with eyes and skin. KEEP OUT OF THE REACH OF CHILDREN. Do not freeze or store above 38°C. Do not mix with other chemicals. Do not release to natural waterways.

Cautions

- Consult SDS for more safety information.
- Inhalation: In high concentrations, vapours may be irritating to the respiratory system.
- Skin contact: May cause skin irritation
- Eye contact: May cause eye irritation
- Ingestion: May cause discomfort if swallowed
- Keep out of reach of children.

TECHNICAL DATA

Physical Properties

Form	Liquid
Colour	Pale Amber
Odour	Mild
pH	9 - 11
Specific Gravity	1.009

(ANSI A118.6, A118.7)

Working Properties

Full cure	24 – 72 Hours
Surface Traffic	6 – 8 Hours

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

INSTALLATIONS

Surface Preparation

Read entire label before using. Use only as directed. Always test in a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Allow new grout installations to cure for a minimum of 72 hours prior to application. Make sure surface is clean and free of waxes and coatings. Sealer may be applied to damp surfaces one hour after standing water has been removed. Surface temperature should be between 10°C and 26°C. Ensure that the area is well-ventilated during application and until the surface is dry. Keep children and pets out of the area until treated surface is dry.

Application

- Ensure cap is closed and sealed, and shake well before use.
- Mask off surfaces not intended to be treated.
- Liberal apply an even coat of STONETECH® BulletProof Sealer using a paint pad, roller, brush or low-pressure sprayer.
- Allow sealer to penetrate the surface for 10-15 minutes. During this time, keep the surface wet with sealer, adding more sealer as needed. DO NOT ALLOW SEALER TO COMPLETELY DRY ON THE SURFACE.
- Thoroughly wipe dry the entire surface with clean absorbent towels.
- A second coat may be needed for porous, absorbent surfaces. If a second coat is required, it should be applied within 30-40 minutes from the initial application as directed in steps 3-5.
- Should a sealer residue appear, rewet the impacted section of the surface with sealer. Agitate the surface with a white nylon scrubbing pad to loosen residue and wipe dry with a clean, absorbent towel.
- A full cure is achieved in 24-72 hours. Use of the treated surface may resume in 6-8 hours. If use of the surface must resume sooner, cover the treated surface with red rosin paper to protect it until full cure has been achieved.
- Clean tools used during application with water.

Cleaning

Clean tools used during application with water.

AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY® materials are available worldwide.

For Distributor information:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

For online distributor information, visit LATICRETE at www.laticrete.com.au

Cost

Contact a LATICRETE Distributor in your area.

MAINTENANCE

Highly alkaline, acidic, ammoniated, or abrasive cleaners are not necessary for daily maintenance and may also degrade the STONETECH® sealer used, adversely affecting stain resistance. Tile and stone routine cleaning with a neutral pH cleaner such as STONETECH Stone & Tile Cleaner is recommended. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. Please note: Prior to using any cleaning material on a tile, stone, etc. installation, test a discrete area or scrap piece of tile to insure desired results. For additional information, please refer to the TDS 1262 Stone and Tile Care Guide.

TECHNICAL SERVICES

Technical assistance

Information is available by calling:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

Fax: 07 3865 2250

Technical and safety literature

To acquire technical and safety literature, please visit our website at www.laticrete.com.au

DISCLAIMER

The information contained in this document is given in good faith and to the best of our knowledge is true and accurate. This information is subject to change without notice and it is the responsibility of the user to obtain up to date and current information. The use of this product is beyond our control and LATICRETE® is not responsible for any loss or damage arising from the incorrect use of this product. Efflorescence is a normal condition of Portland cement and is not covered by any warranty.

LATICRETE Australia Pty Ltd

29 Telford Street, Virginia

QLD 4014 Australia

1800 331 012

www.laticrete.com.au