



**For the Builders
of a Better World™**

RAYSHIELD HEAT REFLECTIVE WATERPROOFING MEMBRANE

Rayshield Heat Reflective Waterproofing Membrane is a one component liquid applied waterproofing membrane that provides excellent reflectance & elastomeric properties designed for exposed applications. Ideal for use on all new & old rooftops, terraces & balconies floors and walls



FEATURES/BENEFITS

- Reduce heat transmission
- Able to accommodate movement & bridge cracks up to 3mm
- Excellent resistance to ultraviolet rays
- Reduce dirt pick up
- Foot trafficable when cured
- High adhesion strength
- Anti-fungi

PACKAGING / COLOUR

25KG/pail; 36 pails per pallet
White & Grey colour

MANUFACTURER

LATICRETE (Malaysia) Sdn Bhd
#18-08, Faber Tower 2, Jalan Desa Bahagia,
Taman Desa,
58100 Kuala Lumpur, Malaysia
Tel: +603 7989 9188 Fax: +603 7972 0331
Website: <https://ma.laticrete.com>

SUITABLE SUBSTRATES

- | | |
|------------------------------------|-----------------------------|
| ▪ Concrete | ▪ Waterproofed glue plywood |
| ▪ Existing steel structure/roofing | ▪ Gypsum wallboard* |
| ▪ Concrete & brick masonry | ▪ Ceramic tile & stone** |
| ▪ Cement mortar beds | ▪ Cement terrazzo** |
| ▪ Cement plaster | ▪ Cement backer board*** |

*Interior applications only

**This type of substrate should be laid with LATICRETE Latex Thin-set Mortar prior to application

***Consult cement backer board manufacturer and LATICRETE Technical Department for specific installation recommendations and to verify acceptability for exterior use

USES

- Interior and exterior
- Rooftops, roof terraces
- Balconies
- Over existing metal roof



This product has been certified green under the Singapore Green Building Council

Approximate Coverage

25kg of Rayshield Heat Reflective Waterproofing Membrane yields approximately 20 - 25m² per 2 coats at a consumption rate of 0.5 – 0.6kg/m²/coat

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years if stored at temperatures > 0°C and < 40°C

Limitations

- DO NOT bond to particle board, luan, Masonite or hardwood surfaces
- DO NOT use over dynamic expansion joints, structural cracks or cracks with vertical differential movement
- DO NOT use over cracks >3mm in width
- DO NOT use as a vapour barrier (especially in steam rooms)
- DO NOT expose to negative hydrostatic pressure, excessive vapour transmission, rubber solvents or ketones
- Consult technical service if to be used as a primary waterproofing membrane over occupied space
- Must be covered with ceramic tile, stone, brick, concrete, screed, terrazzo or other traffic-bearing finish. Use protection board for temporary cover
- Consult technical service if to be used as a primary waterproofing membrane over occupied space
- Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installation where L=span length

Cautions

Consult MSDS for more safety information

- During wet weather, protect finished work until fully cured
- May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water

- Do not take internally
- Keep out of reach of children

TECHNICAL DATA

Performance Properties

Test	Test Method	Results
Tensile Strength	ASTM D2370	>2.1N/mm ²
Elongation at Break	ASTM D2370	>580%
Shore Hardness	ASTM D2240	>68
Crack Bridging	ASTM C836	No cracks @ 2mm
Water Vapour Transmission	ASTM E96	<7g/m ² .24h
Puncture Resistance	ASTM E154	>580N
QUV Accelerated Weathering	ASTM G154	No cracking, blistering & delamination

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions

Working Properties

Rayshield Heat Reflective Waterproofing Membrane can be applied using a paint brush, roller or trowel. Where movement is expected, Anti-Fracture Fabric / reinforcing mesh is recommended to be used to embed within liquid membrane. All areas must have at least two coats to ensure waterproofing capabilities. When using a paint roller, substrate will not show through Rayshield Heat Reflective Waterproofing Membrane.

INSTALLATION

Surface Preparation

Surface temperature must be 8°C - 35°C during application and for 24 hours after installation. All substrates must be structurally sound, clean and free of dirt, oil, grease, paint, laitance, efflorescence, concrete sealers or curing compounds. Make rough or uneven concrete smooth to a wood float or better finish with a LATICRETE underlayment. Do not level with gypsum or asphalt-based products. Pre-wet hot or dry surfaces and sweep off excess water. New

concrete slabs shall be damp cured and a minimum of 14 days old before application.

Pre-treat Cracks, Joints, Coves/Corners & Backer Board Joints

Fill all substrate cracks, cold joints, and control joint to a smooth finish using a LATICRETE Latex Fortified Thin Set Mortar. Alternatively, a liberal coat of Rayshield Heat Reflective Waterproofing Membrane applied with a paint brush or trowel may be used to fill in non-structural joints and cracks less than 3mm. Apply a liberal coat of Rayshield Heat Reflective Waterproofing Membrane approximately 200mm wide over substrate cracks, cold joints, and control joints using a paint brush or roller (heavy napped roller cover).

Fill all substrate coves and floor/wall transitions to a smooth finish and changes in plane using a LATICRETE latex fortified thin-set mortar. Alternatively, a liberal coat of Rayshield Heat Reflective Waterproofing Membrane applied with a paint brush or trowel may be used to fill in cove joints and floor/wall transitions <3mm. Apply a liberal coat of Rayshield Heat Reflective Waterproofing Membrane approximately 200mm wide over substrate coves and floor/wall transitions using a paint brush or roller (heavy napped roller cover). Imbed 150mm Anti-fracture Fabric (if necessary) and then apply a second coat of Rayshield Heat Reflective Waterproofing Membrane.

Pre-Treat Drains

Drains must be of the clamping ring type, with weepers and as per ASME A112.6.3. Apply a liberal coat of Rayshield Heat Reflective Waterproofing Membrane liquid around and over the bottom half of drain clamping ring. Imbed 150mm Anti-fracture Fabric (if necessary) and then apply a second coat of Rayshield Heat Reflective Waterproofing Membrane. When dry, apply LATASIL® where the Rayshield Heat Reflective Waterproofing Membrane meets the drain throat. Install top half of drain clamping ring.

Pre-Treat Penetrations

Allow for a minimum 3mm space between drains, pipes, lights or other penetrations and surrounding ceramic tile, stone or brick. Pack any gaps around

pipes, lights or other penetrations with a LATICRETE Latex fortified thin-set mortar. Apply a liberal coat of Rayshield Heat Reflective Waterproofing Membrane around penetration opening. Imbed 150mm Waterproofing / Reinforcing Fabric and then apply a second coat of Rayshield Heat Reflective Waterproofing Membrane. Bring Rayshield up to level of tile or stone. When dry, seal flashing with LATASIL®

Priming

Substrate must be sound, clean & free of dust, if not it is strongly recommended to use Admix & Primer. Shake thoroughly before using. Pour, mop, or spray primer onto the surface. Apply an even thickness of primer to the prepared substrate using a bristle broom to ensure the primer is absorbed into the substrate, removing any puddles or thick areas.

Allow the primer to dry to a clear film usually 30 – 45 minutes, but less than 3 hours before application of Rayshield Heat Reflective Waterproofing Membrane.

Note: Keep primed surface clean. Do not allow any foot traffic onto surface

Mixing

Use direct from pail

Application

Allow any pre-treated areas to dry to the touch. Apply a liberal coat of Rayshield Heat Reflective Waterproofing Membrane with brush or roller over substrate including pre-treated areas. Then embed the 150mm wide Anti-fracture Fabric and allow to bleed through (if necessary). Let topcoat dry to the touch, approximately 1 – 3 hours at 21°C and 50% RH

Apply second coat of Rayshield Heat Reflective Waterproofing Membrane. When second coat has dried to the touch, inspect final surface for pinholes, voids, thin spot or other defects. Use additional Rayshield Heat Reflective Waterproofing Membrane to seal defects. Provide protection for newly installed membrane, even if covered with a thin bed ceramic tile, stone or brick installation, against exposure to rain or other water for a minimum of 24 hours at 21°C and 50% RH.

Expansion Joints

Ceramic tile, stone and brick installations must include expansion at coves, corners, other changes in substrate plane and over any expansion joints in the substrate. Expansion joints in ceramic tile, stone or brickwork are also required at perimeters at restraining surfaces, at penetrations and at the intervals described in the Tile Council of North America (TCNA) Handbook Installation Method EJ171. Use LATASIL and backer rod

Cleaning

While wet, Rayshield Heat Reflective Waterproofing Membrane can be washed using tools with water

AVAILABILITY AND COST

Availability

LATICRETE materials are available worldwide

For distributor information, call:

Telephone: +603 7989 9188

Fax: +603 7972 0331

For online distributor information, visit LATICRETE at <https://ma.laticrete.com>

Cost

Contact a LATICRETE distributor in your area

WARRANTY

LATICRETE (Malaysia) Sdn Bhd warrants that Rayshield Heat Reflective Waterproofing Membrane is free from manufacturing defects and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subjected to terms and conditions stated

MAINTENANCE

LATICRETE grouts require routine cleaning with a neutral pH detergent and water. All stone and tiles should be maintained and sealed with STONETECH® products as appropriate for the specific tile / stone and installation situation

All other LATICRETE materials require no maintenance, but installation performance and durability may depend on properly maintaining products supplied by other manufacturers

TECHNICAL SERVICE/CONTACT

Technical Assistance

Information is available by calling:

LATICRETE (Malaysia) Sdn Bhd
#18-08, Faber Tower 2, Jalan Desa Bahagia,
Taman Desa, 58100 Kuala Lumpur,
Malaysia

Telephone: +603 7989 9188

Fax: +603 7972 0331

Email: enquiry@laticrete.com.my

Technical and safety literature

To acquire technical and safety literature, please visit our website at <https://ma.laticrete.com>