



Globally Proven  
Construction Solutions

## 4237 Latex Additive

4237 Latex Additive is a specially designed latex additive for use with 211 Powder to make high strength latex thin-set bed up to 3 mm and medium bed up to 15 mm mortars.

For installing all types of ceramic tile and natural stone and agglomerates. Also, for use with portland cement to make slurry bond coats for mortar beds and with thin set mortars to give improved performance and longer open time.



### ADVANTAGES

- Superior bond strength—250% greater than ANSI A118.4 (American National Standard Specification for Latex Portland Cement Mortar)
- Flexible and shock resistant; rated for extra heavy traffic conditions
- Weather and frost resistant for interior and exterior use in all types of climates
- Proven performance; used in all types of applications for over 50 years
- Safe, economical, and easy to use; non-hazardous, non-flammable

*To achieve longer open time under tropical or desert conditions, contact your local LATICRETE Technical Services office. 254 Platinum is an approved substitute for 211 Powder mixed with 4237 Latex Additive (please refer data-sheet 254.me for details).*

### MANUFACTURER

**LATICRETE Middle East LLC.**  
P.O. Box. 86028, Ras Al Khaimah  
United Arab Emirates  
Telephone: + 971 7 244 6396  
Fax: + 971 7 244 5915  
internet: www.laticrete.me

### USES

- Installation of ceramic tile, brick, stone, agglomerate and glass mosaic over cement and masonry type surfaces.
- 4237 Latex Additive offers the speed and economy of adhesives with the permanent, water resistant dependability of Portland cement.
- Can also be mixed with PERMACOLOR® Grout for the installation of paper face mounted glass mosaic tile for the one step method.
- Interior, exterior, wet & non-wet areas, submerged areas, etc....

### STANDARDS

#### Applicable Standards

(When mixed with 211 Crete Filler Powder)

- ANSI A 118.4, ANSI A 118.11, ANSI A 118.15
- EN 12004 (C2TE S1 & C2TF S1)
- BS5980: 1980 (Type 3, Class AA)

#### GREENGUARD CERTIFIED



#### DCLD CERTIFIED



Please see the technical data

**Packaging,**

20 L Pail,  
Pallet: 36 per pallet

**Suitable Substrates,**

- Concrete
- Brick masonry
- Concrete masonry
- Cement mortar beds
- Gypsum wallboard (interior only)
- Cement terrazzo
- Cement plaster
- Cement backer board\*
- Ceramic tile and stone

\* Consult cement backer board manufacturer for specific installation recommendations and to verify acceptability for exterior use.

**Approximate Coverage**

Per 20 kg bag of LATICRETE® 211 Crete Filler Powder	
Notch Trowel	Coverage (M <sup>2</sup> )
6mm x 6mm	6.5 – 7.75
6mm x 9mm	5.25 – 6.5

**Shelf Life**

Factory sealed containers of this product are guaranteed to be of first quality for five (5) years if stored indoors and off the ground at temperatures >32°F (0°C) and <110°F (43°C).

**Limitations**

- Use LATAPOXY® 300 Adhesive for installing green marble, water sensitive stone and agglomerates and resin backed tile or stone.
- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Use a white thin set mortar when installing white or light colored natural stone.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).

**Cautions**

Consult MSDS for more safety information.

- During cold weather, protect finished work from traffic until fully cured.
- Wait 14 days after the final grouting period before filing water features with water at 70°F (21°C).
- Keep out of reach of children.

**TECHNICAL DATA****Certification/ Approvals**

**GREENGUARD:** This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program for Chemical Emissions for Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment

**DCLD:** This product has been certified for Low Emitting Materials by Dubai Central Laboratory Department (DCLD) of Dubai Municipality. No.CL20020733: 2017 Al Sa'fat Dubai Green Building Evaluation System.

**Performance Properties**

4237 Latex Additive mixed with 211 Powder

Test/Test Method	Result
Shear Bond, Porcelain Tile, 28-day cure ANSI A118.4- 5.2.4	2.9 MPa
Shear Bond, Porcelain Tile, Water Immersion ANSI A118.4- 5.2.3	2.1 MPa
Water Absorption ANSI A118.6-4.4	4% max.
Compressive Strength ASTM C109	>20 MPa
TCA Service Rating ASTM C-627	Extra Heavy
Tensile Adhesion strength as per ISO 13007-2:2013	>2.6 MPa

**Working Properties**

4237 Latex Additive mixed with 211 Powder at 25°C

Open Time	50 minutes
Pot Life	5 hours
Time to Heavy Traffic	24 hours
Wet Density	1550 kg/m <sup>3</sup>

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

**INSTALLATION****Surface Preparation**

All surfaces should be between 4°C and 32°C and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with Latex Portland Cement underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface.

*Note: Latex Portland Cement Mortars do not require minimum cure time for concrete slabs. All slabs must be*

plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "Requirements for Movement Joints: Preparations by Other Trades" or TCNA detail EJ-171 "Movement Joints—Vertical & Horizontal". Do not cover expansion joints with mortar.

### Mixing

#### **Stir 4237 Latex Additive thoroughly before use.**

Use approximately 5 Liters of 4237 Latex Additive to 20kg of 211 Powder. Place 4237 Latex Additive in a clean plastic pail. Do not dilute. Add 211 Powder to 4237 Latex Additive and mix to a smooth, trowelable consistency. Allow mortar to slake for 5–10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

*Note: For the one-step installation of paper-face mounted glass mosaic tile, mix 2.5 L of 4237 Latex Additive with 10 kg of PERMACOLOR® Grout<sup>†</sup>. See TDS 145 "Installation of Glass Mosaic Tile", available at [www.laticrete.com](http://www.laticrete.com) for more information.*

### Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side.

*Note: Use the proper sized notched trowel to insure full bedding of the tile. It is essential that enough mortar is used to completely cover the back of the tile with a minimum 2 mm to 3mm uniform thickness. Spread as much mortar as can be covered with tile in 15–20 minutes. Back butter large tiles >200 mm x 200 mm to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to imbed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile.*

### Grouting

Grout installation after a minimum of 24 hours curing time at 21°C. Grout with SPECTRALOCK PRO Premium Grout, PERMACOLOR Grout, 1500 Sanded Grout or 1600 Unsanded Grout gauged with 1776 Grout Enhancer or with water.

*Cold Weather Note: The setting of Portland cement mortars and grouts are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather. For faster setting mortar use Thin-Sets with 101 Rapid Latex Admix. Do not set tile when surface temperature is below freezing or when substrate is frozen.*

*Hot Weather Note: The evaporation of moisture in Portland cement mortars is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread mortar and finished work when installing in temperatures over 35°C.*

### Cleaning

Clean tools and tile work with water while mortar is fresh.

## AVAILABILITY AND COST

### Availability

LATICRETE® materials are available worldwide.

For distributor information, please contact us by email at: [enquiry@laticrete.me](mailto:enquiry@laticrete.me) or, visit [www.laticrete.me](http://www.laticrete.me)

### Cost

Contact a LATICRETE® closer distributor to obtain complete information and cost.

## WARRANTY

The supplier warrants that the product will not deteriorate under normal conditions and use. The warranty validity of one (1) year. Contact Technical Support for further information

## MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. LATICRETE® products are of high quality designed to achieve lasting installations and avoid maintenance, however performance and durability may depend on properly maintaining products, depending of the cleaning products used.

## TECHNICAL SERVICES

### Technical assistance

For information contact us by email at: [enquiry@laticrete.me](mailto:enquiry@laticrete.me)

### Technical and safety literature

To obtain technical and safety literature, please visit our website at: [www.laticrete.me](http://www.laticrete.me)

**Warning:** The information and the instructions in the data sheet, although based on knowledge gained through years of applications, are indicative. LATICRETE® unable to directly control the installation conditions and modalities of application of products, do not assume any liability arising from their implementation. Those who want to use the LATICRETE® products must conduct adequate tests to determine the site specifications. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation method and site conditions.

<sup>†</sup>United States Invention Patent No.: 6881768 (and other Patents)

<sup>^</sup>United States Invention Patent No.: 6784229 (and other Patents)