



Globally Proven  
Construction Solutions

## LATAFINISH Wall Putty - Coarse Finish

LATAFINISH Grey Coarse Finish Wall Putty is a cement-based powder. After mixing with recommended quantity of water it forms a paste, which is used as a base coat. It covers surface unevenness and can be used as a layer before using LATAFINISH Wall Putty fine finish.



### ADVANTAGES

- Easy to apply.
- Water Resistance.
- Anti-fungal.
- Good Compressive Strength.
- Increases Paint coverage
- Covers undulations of plastered surfaces.
- Give sound base for further putty applications

### MANUFACTURER

**LATICRETE Middle East LLC.**  
P.O. Box. 86028, Ras Al Khaimah  
United Arab Emirates  
Toll Free (with in UAE) 800 5632  
Telephone: + 971 7 244 6396  
Fax: + 971 7 244 5915  
[www.laticrete.me](http://www.laticrete.me)

### USES

- Designed for interior and exterior surfaces.
- To make uneven surfaces to even and smooth

### APPLICABLE STANDARD / CERTIFICATIONS

- EN 1015:12 & EN 1015:1
- BS 4551:1



This product has been certified for Low Emitting Materials by Dubai Central Laboratory Department (DCLD) of Dubai Municipality. No.CL20020733: 2017 Al Sa'fat Dubai Green Building Evaluation System.

*Please see the technical data*

**Packaging,**

20 kg Bag – 72 bags per pallet

5 Kg – 4 pouches per carton/ 40 cartons per pallet

1 Kg – 10 pouches per carton/ 48 cartons per pallet

**Color:** Grey

**Approximate Coverage**

3 to 4 Sq.ft (0.28 to 0.37 m<sup>2</sup>) per Kg of Powder when mixed with water for total approximate thickness of 3 mm.

[ 20Kg bag of Powder will cover 5.6 to 7.4 m<sup>2</sup>]

**Shelf Life**

Factory sealed bags of this product are guaranteed to be of first quality for 12 (Twelve) months\* if stored off the ground in a dry area.

\* High humidity will reduce the shelf life of bagged product.

**Limitations**

- Do not directly apply on the fungus and moss affected areas.
- Do not apply directly on the dust, loosely bonded particles, oil, Grease etc affected surfaces

Note: Surfaces must be two coated cement and smooth plaster, structurally sound and stable.

**Cautions**

- Though it contains non-toxic material but still care should be taken to avoid dust inhalation while mixing and handling. In case of contact with eyes or mouth, flush thoroughly with plenty of water.
- Do not take internally. Avoid breathing dust.
- Keep out of reach of children

**TECHNICAL DATA****Applicable Standard**

HDB Singapore.

Test	Specification of HDB standard	Results	Standard method
Tensile adhesion strength @ 14 day	≥ 0.8 MPa	1.2 MPa	EN 1015:12
Compressive Strength @ 28 days	7 to 12 MPa	8 MPa	EN 1015:11
Water	>95%		
Retentivity		99%	BS 4551:1
Pot life	---	2-3hrs	---

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

**INSTALLATION****Preparation**

All Surfaces should be between 40°F (4°C) and 90°F (32°C) temp. It should be free from all dirt, oil, grease, and loose sand particles. If it is old painted wall/lime washed wall then first scratch old surface. Dry and absorbent surfaces should be moistened/pre-wet with clean water.

**Mixing**

Use approximately 4.5 to 6 L of fresh water for 20 kg l Latafinish® Grey coarse putty. I.e. Water to Powder ratio is approx 25:100. Mix thoroughly till uniform (free from bubbles and lumps) paste occurs. Allow paste to slake for 5-10 minutes. Adjust consistency if necessary. Remix and apply with iron trowel/blades.

**Application**

Apply one coat of the above paste on to the substrate with the trowel. The thickness allowed in one coat application is 3-5 mm. Ensure that the second coat application should be done when the first coat is totally dried. The second coat can be done with either Latafinish Wall Putty or Coarse Putty. Always prepare a required quantity of putty paste and use it within 2-3 hrs.

**AVAILABILITY AND COST****Availability**

LATICRETE® materials are available worldwide. For distributor information, please contact LATICRETE Telephone: For on-line distributor information, visit [www.laticrete.com](http://www.laticrete.com)

**Cost**

Contact a LATICRETE® closer distributor to obtain complete information and cost.

**WARRANTY**

The supplier warrants this product will not deteriorate under normal conditions and use, the warranty validity of one (1) year. The product subject to the terms and conditions stated in the LATICRETE® Product Warranty.

**TECHNICAL SERVICES****Technical assistance**

For information contact:  
[enquiry@laticrete.me](mailto:enquiry@laticrete.me)

**Technical and safety literature**

To obtain technical and safety literature, please visit our website at [www.me.laticrete.com](http://www.me.laticrete.com)