



Globally Proven
Construction Solutions

Hydrolinate Waterproofing Membrane

LATICRETE® Hydrolinate Waterproofing Membrane system for below grade construction is designed to provide flexibility to perform over a wide range of installation technique, weather, substrates and conditions.. LATICRETE Hydrolinate Waterproofing Membrane is a special composite high performance water, vapour and gas proofing membrane comprising of a thick HDPE (High Density Polyethylene) layer, a unique pressure sensitive adhesive and a trafficable weather resistant protective coating. LATICRETE® Hydrolinate Waterproofing Membrane is a pre-applied type of membrane that bonds intimately with fresh concrete to form a continuous bond and prevent migration of water around the structure.



FEATURES/BENEFITS

- Complies with international code of practices
- Achieved Grade 1, 2 and 3 waterproofing protection under BS8102 : 2009
- Pre-applied, completely seals the concrete from water ingress
- Excellent chemical resistance against aggressive elements
- Membrane not affected by ground settlement
- Provides a barrier to underground water, vapour and gas
- Trafficable immediately after installation and ready for immediate placing of reinforcement
- Unaffected by weathering
- Safe and non-hazardous application

USES

- Basement Slab and Wall
- Civil Tunnels
- Earth Retaining Structure including Blind Side application etc

MANUFACTURER

LATICRETE South East Asia Pte Ltd
No. 38 Sungei Kadut Street 2 (Level 2, A3) Singapore 729245
Telephone: +65 6515 3028 Fax: +65 6515 3037
Internet: se.laticrete.com

STANDARDS/CERTIFICATIONS

- ASTM D412
- ASTM D903
- DIN 16726
- ASTM E154

Packaging

LATICRETE® Hydrolinate Waterproofing Membrane comes in 20m x 1.20m x 1.20mm per roll.

LATICRETE® Hydrolinate Waterproofing Membrane Tapes comes in 50m x 120mm per roll.

Coverage

LATICRETE® Hydrolinate Waterproofing Membrane yields approximately 24 m² per roll

TECHNICAL DATA

Performance Properties

Test	Test Method	Results
Tensile Strength	ASTM D412	≥ 25 N/mm ²
Elongation	ASTM D412	≥ 500%
Peel Adhesion	ASTM D903	≥ 1,000 N/mm
Hydrostatic Resistance @ 7 bars	DIN 16726	Pass
Puncture Resistance	ASTM E154	≥ 900 N

INSTALLATION

Horizontal application

Place the membrane with the removable plastic sheet facing up. End laps should be staggered to avoid a buildup of layers. Overlap subsequent sheet 75mm along the selvedge edge. For end lap, overlap a minimum of 75mm and apply LATICRETE® Hydrolinate Waterproofing Membrane Tape. During application, ensure the underside of the succeeding sheet is clean, dry and free from contamination before attempting to overlap. Ensure a continuous bond is achieved and roll firmly. On completion of installation, remove the release liner from the membrane.

Vertical application for confine space

Place the membrane with the HDPE side onto the substrate. Secure the membrane by mechanical fastening along the overlapping edge of the membrane. Apply subsequent sheet along these edges to fully cover the fasteners. Ensure a continuous bond along the laps before removing the membrane release liner. Any additional fastener on the membrane surface which are not covered by the subsequent sheet shall be covered over by LATICRETE® Hydrolinate Waterproofing Membrane tape.

Vertical application with working space

For application onto external side of retaining wall with working space, use LATICRETE® Hydrolinate Waterproofing Membrane post applied membrane. The surface of the

substrate to be applied shall be clean, dry and free from contamination. Remove the plastic release liner and adhere the membrane directly onto the concrete substrate. Overlap subsequent sheet by 75mm for both side and end laps.

Pouring of concrete

Ensure all the plastic released liners are removed from the membrane. It is recommended that the concrete be poured within 48 days after the complete removal of the release liner.

AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY materials are available worldwide.

For distributor information, call:

Telephone: (65) 6515-3028

Fax: (65) 6515-3037

For on-line distributor information, visit LATICRETE at se.laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

WARRANTY

LATICRETE South East Asia Pte Ltd warrants that Hydrolinate Waterproofing Membrane is free from manufacturing defects and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subject to the terms and conditions stated in Data Sheet.

TECHNICAL SERVICES/ CONTACT

Technical Assistance

Information is available by calling:

LATICRETE South East Asia Pte Ltd

No. 38 Sungei Kadut Street 2

(Level 2, A3)

Singapore 729245

Telephone: (65) 6515-3028

Fax: (65) 6515-3037

Email: enquiry@laticrete.com.sg

Technical and safety literature

To acquire technical and safety literature, please visit our website at se.laticrete.com