



Pigments

Pigments are designed to be used exclusively with Guard PA SB, Guard PA XT or Guard PA Pure polyaspartic coatings. Available in 14 standard colors, these materials are manufactured through a proprietary process in which raw pigment elements are ground and subsequently combined with the highest quality polyaspartic resins available. Once ready for use, these concentrated pigments are dispersed directly into short-filled part A pigment base.

**For the Builders
of a Better World™**



FEATURES/BENEFITS

- 14 standard colors, including safety colors
- UV stable, suitable for exterior applications
- Excellent color hide and retention
- Easy to use on-site color dispersion system

USES

- Suitable for interior or exterior applications

MANUFACTURER/ DISTRIBUTED BY

LATICRETE South East Asia Pte Ltd

No. 38 Sungei Kadut Street 2 (Level 2, A3) Singapore 729245

Telephone: +65 6515 3028 Fax: +65 6515 3037

Internet: se.laticrete.com

Suitable Substrates

As per LATICRETE Polyaspartic Coating

Packaging

- 1 qt (0.9ℓ) for 0.75 gal (2.8ℓ) part A base
- 1.25 gal (4.7ℓ) for 3.75 gal (14.2ℓ) pigment base

Available in 14 standard colors including safety colors pre-dispersed form upon request. Guard PA SB polyaspartic coating is available in a White.

Approximate Coverage

See applicable LATICRETE Polyaspartic Coatings coverage chart

Shelf Life

12 months unopened. Store at $\geq 0^{\circ}\text{C}$ and $\leq 40^{\circ}\text{C}$ in a covered area (out of the sun). Maintain a consistent storage temperature prior to application. Material should be kept in a cool dry place prior to application.

Limitations

Refer to data sheet for applicable LATICRETE Polyaspartic Coatings

Cautions

- Refer to Safety Data Sheet (SDS)

Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

INSTALLATION

Mixing

Note: Maintain a consistent storage temperature prior to application. Material should be kept in a cool dry place prior to application. Use only with Guard PA SB, Guard PA XT or Guard PA Pure polyaspartic coatings.

Pigmented Coatings

Add full contents of Pigments directly into short filled Part A Tint Base. Mix pigment into Part A with a slow speed drill mixer for 2 minutes to fully disperse the resin pigments. Failure to properly mix pigments may lead to an inconsistent finish and reduced product performance.

AVAILABILITY AND COST

Availability

LATICRETE® materials are available worldwide. For distributor information, call:

Telephone: (65) 6515-3028

Fax: (65) 6515-3037

For on-line distributor information, visit LATICRETE at se.laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

WARRANTY

Subject to the conditions and limitations stated below, LATICRETE South East Asia Pte Ltd warrants that its products will be free from manufacturing defects and will not break down or deteriorate under normal usage for a period of one (1) year from the date of purchase when installed in accordance with the written specifications of LATICRETE and industry standard guidelines.

MAINTENANCE

The long term performance, appearance, and life expectancy of wear surface products are critically dependence upon a good routine maintenance program designed specifically for the installed wear surface. LATICRETE polyaspartic and epoxy floor coating systems are nonporous, causing dirt and contaminants to remain on the surface. The use of properly placed walk-off mats, inside and outside, will help increase the life of the floor. Recommend maintenance program consist on frequent and through cleaning utilizing a neutral pH cleaner (e.g. Simple Green®). Frequency of washing will vary depending on floor usage type, traffic and age.

TECHNICAL SERVICES/ CONTACT

Technical Assistance

Information is available by calling:

LATICRETE South East Asia Pte Ltd
No. 38 Sungei Kadut Street 2
(Level 2, A3)
Singapore 729245
Telephone: (65) 6515-3028
Fax: (65) 6515-3037
Email: enquiry@laticrete.com.sg

Technical and safety literature

To acquire technical and safety literature, please visit our website at se.laticrete.com

Disclaimer

LATICRETE is not responsible for product use beyond its intended application. Liability is limited to replacing defective materials. We are not responsible for any loss or damage resulting from improper use. Product specifications are subject to change without notice. For the most up-to-date information, please visit our website at se.laticrete.com.